

ANTIROCK

 TECHNICAL DATA SHEET
100322SCAN1E
 (supersedes 031030CAN1E)

DESCRIPTION

The **ANTIROCK** waterproofing membrane is composed of a non-woven polyester reinforcement and SBS modified bitumen. Its underface is protected by a thermofusible plastic film and its top face is covered with mineral granules.

The **ANTIROCK** membrane is designed to waterproof civil engineering structures. It must be installed by thermofusion on dry and clean surfaces previously primed with **ANTIROCK PRIMER** or **ANTIROCK EMULSION PRIMER**.

For complete information on application and systems, please consult our specification manual.

PROPERTIES

Properties	Standards	ANTIROCK	
Thickness	-	4.5 mm	
Dimension	-	8 X 1 m	200 x 1 m
Roll Weight	-	45 kg	1150 kg
Top face	-	Granules	
Underface	-	Thermofusible plastic film	
Reinforcement	-	Non-woven polyester	
Storage	-	Upright on pallet	
Stain energy, MD/XD	CAN-CSGB-37.56-M 9 TH draft	9.0 / 7.0 kN/m	
Breaking strength, MD/XD	CAN-CSGB-37.56-M 9 TH draft	17 / 12.5 kN/m	
Ultimate elongation, MD/XD	CAN-CSGB-37.56-M 9 TH draft	60 / 65 %	
Cold bending	CAN-CSGB-37.56-M 9 TH draft	-30 °C	
Static puncture	CAN-CSGB-37.56-M 9 TH draft	400 N	

(All values are nominal)