

■ Calgary ■ Edmonton ■ London ■ Moncton ■ Montreal ■ Ottawa ■ Quebec ■ Saskatoon ■ Toronto ■ Vancouver ■ Winnipeg

MAMMOUTH ELASTOCOL 500

Description: *ELASTOCOL 500* is a primer made with SBS modified bitumen, fast-evaporating solvents and adhesive enhancing additives. It is required to prime most surfaces such as concrete, metal and gypsum board substrates in order to improve the adhesion of torch-applied waterproofing membranes.

Application: *ELASTOCOL 500* can be applied with a brush, roller or sprayer. It must be thoroughly dry before applying the waterproofing membrane.

Average coverage: 0.15 to 0.25 L/m² (0,375 à 0,625 gal US/100 ft²)

Amount used could increase depending on porosity of the surface.

WARNING: Do not accelerate drying of *ELASTOCOL 500* by heating it with a torch.

Properties:

ELASTOCOL 500 meets the requirements of the ASTM D41 standard.

Properties	ELASTOCOL 500
Specific gravity at 20°C (kg/L)	0.91
Colour	Black
Solids by Weight (%)	35
Viscosity, Brookfield at 25°C (cP)	50
Flash point (ASTM D-93)	-3°C (26°F)
Drying time	1 to 12 hours

(All values are nominal)

Packaging:

19 L pails, 200 L drums and 350g spray cans.

Shelf life: Up to 5 years in original sealed containers, in cool and ventilated area.

Cleaning:

Tools can be cleaned with petroleum solvents such as mineral spirits, varsol, xylene, etc.

Precautions:

ELASTOCOL 500 is a flammable product.

Store away from direct sunlight and open flame. Keep ignition sources away during application and until solvent has evaporated. Harmful if inhaled, swallowed or when in contact with the skin. In closed area, ventilate carefully using mechanical means if necessary. Do not pour residues in drains.

CONSULT THE MATERIAL SAFETY DATA SHEET PRIOR TO USE.

